

Brutus[®] AAA

Shielded Metal Arc Welding (SMAW – Stick)

For dissimilar and all categories of steel–tool, high alloy, nickel alloy, stainless, manganese and cast steels.

Features

- 35% Elongation
- Strength 127,000psi
- Easy Strike and Restrike
- No Spatter / Easy Slag Release
- Exceptionally Smooth Bead
- Spray-Type Arc With Low Heat
- Excellent Undercoating For Hardfacing
- Wear and Shock Resistant
- Ideal For Dissimilar Steels
- Ductile, Crack Resistant Deposit
- Use for Broken Stud Extraction (See Thread Repair & Bolt Removal)

Characteristics

Brutus AAA has superior wear, shock and corrosion resistance and it can be used for joining dissimilar steels. In addition, **Brutus AAA** has a special flux coating that gives it superior operating characteristics, allowing the welder to produce an unusually strong, smooth weld deposit with minimum effort.

Brutus AAA's ease of application makes it especially suitable where precise weld control and appearance are important. Thin sections and delicate parts can be repaired easily. It gives excellent results on dies, tools, molds, gears and exposed food handling equipment. Its high strength and ductility make it useful in almost all repairs of similar or dissimilar steels.

Technical


Size and Amps AC/DC ±30%

Inches	3/32	1/8	5/32
(mm)	(2.4)	(3.2)	(4.0)
Amps	65	95	120

With DC use reverse polarity. (DCEP)

Application

- Clean weld area.
- Bevel heavy sections.
- Preheat high alloys and heavy sections to 400°F (240°C).
- Use short arc.
- Tilt electrode 15° in direction of travel.
- For rapid filleting, increase amps and drag electrode at 45°.
- Remove slag between passes.

 [Click for Product Demonstrations](#)

Brutus[®] A

Shielded Metal Arc Welding (SMAW – Stick)

For dissimilar and all categories of steel–tool, high alloy, nickel alloy, stainless, manganese and cast steels.

Features

- Superior Strength 125,000 psi
- Easy To Use In All Positions
- Wear and Shock Resistant
- Prevents Undercutting
- 35% Elongation (Ductile)
- Low Heat Requirements
- Excellent Corrosion Resistance
- No Spatter
- Ideal For Dissimilar Steels
- Use For Broken Stud Extraction (See Thread Repair & Bolt Removal)

Characteristics

Brutus A is for the maintenance welder who often does not know the type of steel he is welding or must weld dissimilar steels. **Brutus A** is easy to weld in all positions and produces sound super–strength yet ductile welds. These fully machinable deposits have no hard spots.

In many cases the maintenance welder is unable to weld on both sides of the joint. In these circumstances the use of **Brutus A** with its superior strength and ductility is essential.

Excellent for use on tools, dies, pressure vessels, springs, stainless steels and dissimilar combinations. Ideal to build up shafting, agitator blades and for use on construction and mining equipment.

Technical

Size and Amps AC/DC ±30%

Inches	1/16	3/32	1/8	5/32
(mm)	(1.6)	(2.4)	(3.2)	(4.0)
Amps	35	70	100	120

With DC use reverse polarity. (DCEP)

Application

- Bevel heavy sections.
- Hold a short arc or drag.
- Use stringer beads.
- For high alloys and heavy sections preheat to 400°F (240°C), skip weld, and peen to avoid internal stress.



[Click for Product Demonstrations](#)